

CONTUR - FR

KM
kinnamark






CONTUR - FR

Art. nr.	101043
Composition	100% Polyester FR
Width	300 cm
Weight	273 gr./m ²
Repeat (+/- 2%)	0 cm
Colorfastness to light	≥ 5 SS EN ISO 105-B02 (Scale 1-8)
Colorfastness to washing	5 SS EN ISO 105-C06 (Scale 1-5)

Care Instruction	
Shrinkage	1%
Certificate	Oeko -Tex Standard 100
Flame retardant according to:	EN 13772:2011 Class 1 EN 1011:1995+A1:2005
Acoustics	Measurement of sound absorption in a reverberation room: EN ISO 354:2003. Ration of sound absorption EN ISO 11654:1997 $\alpha_w = 0,65$ / Class C





CONTUR - FR

Art. nr.	101043
Composition	100% Polyester FR
Width	300 cm
Weight	273 gr./m ²
Repeat (+/- 2%)	0 cm
Colorfastness to light	≥ 5 SS EN ISO 105-B02 (Scale 1-8)
Colorfastness to washing	5 SS EN ISO 105-C06 (Scale 1-5)

Care Instruction	
Shrinkage	1%
Certificate	Oeko -Tex Standard 100
Flame retardant according to:	EN 13772:2011 Class 1 EN 1011:1995+A1:2005
Acoustics	Measurement of sound absorption in a reverberation room: EN ISO 354:2003. Ration of sound absorption EN ISO 11654:1997 $\alpha_w = 0,65$ / Class C

